

ScotchÒ

General Purpose Filament Reinforced Tape - Cross-Weave 8959

Product Data Sheet

Updated : July 2000
Supersedes : February 1999

Product Description

8959 is a general purpose tape reinforced with two-directional (cross weave) glass filaments.

The Scotchpro™ polypropylene backing provides excellent abrasion, moisture and scuff resistance. The adhesive is specially formulated to provide good adhesion to fibreboard surfaces.

Physical Properties

Not for specification purposes

| | |
|---------------------------|--|
| Adhesive Type | Pressure Sensitive Hot Melt Solvent Free (Synthetic Rubber Resin) |
| Backing | Scotchpro™ Polypropylene |
| Reinforcement | Glass Filament |
| Total Thickness | 145 micron |
| Colour | Transparent |
| Storage Conditions | Store behind present stock, in a clean dry place. Temperature of 64 - 70°F (18-21°C) & 40-50% Relative Humidity are recommended. Under correct storage conditions the tape maintains its characteristics for one year (shelf life). Rotate your stock. |

Application

An extensive line of application equipment including hand held manual dispensers and semi-automatic L-Clip applicator.

Application of 8959 is most easily accomplished at room temperature. At colder temperatures, approaching 32°F (0°C), the adhesive becomes more firm.

Once applied, 8959 performs well throughout the normal temperature ranges typically encountered by packaged products in shipping and storage environments.

Date : July 2000
 Scotch® General Purpose
 Filament Reinforced Tape
 Cross-Weave 8959

Performance Characteristics
 Not for specification purposes

| | |
|--|----------------|
| Adhesion to Steel AFERA 4001 | 8.0 N/10 mm |
| Tensile Strength AFERA 4004 | 300 N/10mm |
| Elongation at Break AFERA 4005 | 10 % |
| Static Shear | 4,500+ minutes |

3M and Scotch are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Tapes & Adhesives

© 3M United Kingdom PLC 1996

3M United Kingdom PLC
 3M House,
 28 Great Jackson Street,
 Manchester,
 M15 4PA

Product Information :
 Tel 0870 60 800 50
 Fax 0870 60 700 99

3M Ireland
 3M House, Adelphi Centre,
 Upper Georges Street,
 Dun Laoghaire, Co. Dublin,
 Ireland

Customer Service :
 Tel (01) 280 3555
 Fax (01) 280 3509