



Double Coated Tapes

9731 • 9731RW

Technical Data

September, 2002

Product Description

3M™ Double Coated Tapes 9731 and 9731RW have a firm, silicone pressure sensitive adhesive coated on one side of a polyester film carrier and a high performance acrylic adhesive coated on the other side of the carrier. The silicone adhesive features strong holding power to various silicone surfaces, good temperature performance and good solvent resistance. This tape also features high adhesion of the acrylic adhesive to a variety of surfaces along with good high temperature performance and good solvent resistance.

Constructions

	Faceside^{1,4} Adhesive Type/ Thickness	Carrier Type/ Thickness	Backside^{2,4} Adhesive Type/ Thickness	Liner Color, Type, Print	Liner Caliper
Tape 9731	350/ 0.0016" (0.041mm)	Clear PET 0.001" (0.025mm)	Silicone Adhesive/ (0.0029mm) (0.074mm)	Faceside liner – Tan, Polycoated Kraft, no print Backside liner – Clear, PET	0.005" (0.13mm)/ 0.004" (0.10mm)
Tape 9731RW	Silicone Adhesive/ (0.0029mm) (0.074mm)	Clear PET ³ 0.001" (0.025mm)	350/ 0.0016" (0.041mm)	Faceside liner – Clear, PET Backside liner – Tan, Polycoated Kraft, no print	0.004" (0.10mm)/ 0.005" (0.13mm)

Note 1: Faceside adhesive is on the interior of the roll, exposed when unwound.

Note 2: Backside adhesive is on the exterior of the roll, exposed when liner is removed.

Note 3: PET (Polyester).

Note 4: The caliper listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc.

3M™ Double Coated Tapes

9731 • 9731RW

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product Number	Tape 9731/9731RW Silicone Adhesive	Tape 9731/9731RW Acrylic Adhesive
Adhesion to stainless steel		
ASTM D3330 - 90 degree	Oz/in (N/100 mm)	Oz/in (N/100 mm)
- 15 minute RT	40 (44)	71 (77)
- 72 hour RT	42 (45)	93 (101)
- 72 hour 158°F	48 (52)	121 (132)
Adhesion to other surfaces		
ASTM D3330 - 90 degree, 2 mil al foil, 72 hour RT	Oz/in (N/100 mm)	Oz/in (N/100 mm)
ABS	39 (43)	74 (81)
Polycarbonate	42 (45)	60 (65)
Polypropylene	40 (44)	44 (48)
Shear Strength		
ASTM D3654 modified - (.5 inch ² sample size)	minutes	minutes
1000 grams at 72°F	+10,000	6090
500 grams at 158°F	+10,000	+10,000
Dielectric Strength		
ASTM D1000 RMS Voltage/Thickness	8000 Volts	
Resistivity (ASTM D257) @ 70°F, 50% RH		
Volume	3.4 x 10 ¹⁵ Ω-cm	
Silicone Adhesive Surface	2.6 x 10 ¹⁵ Ω-cm	
Acrylic Adhesive Surface	7.4 x 10 ¹⁵ Ω-cm	
Relative High Temperature Operating Ranges		
Long Term (days, weeks)	250°F (121°C)	
Short Term (minutes, hours)	350°F (177°C)	
Shelf Life of Tape in Roll Form	12 months from date of manufacture when stored in original cartons at 70°F (21°C) and 50% relative humidity.	

Available Sizes

(Subject to Minimum order requirements)

Maximum Length	
1/4" to 3/8"	36 yds. (32.9 m)
1" to 38"	108 yds. (98.9 m)
Available Widths	
Minimum	1/4" (6.35 mm)
Maximum	38" (965 mm)
Normal Slitting Tolerance	± 1/32 in. (0.08 mm)
Core Size	3.0 in. (76.2 mm)

3M™ Double Coated Tapes

9731 • 9731RW

Application Techniques	<p>Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength.</p> <p>To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane. Note: Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. These cleaning recommendations may not be in compliance with the rules of certain air quality management districts in California; consult applicable rules before use.</p> <p>Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.</p>
General Information	<p>Silicone adhesive provides good bond to silicone rubber.</p> <p>3M™ Adhesive 350 provides very high adhesion to a wide variety of materials, excellent shear holding power, high temperature resistance and excellent UV resistance.</p>
Features	<p>A thin polyester carrier in the products provides dimensional stability and improved handling with ease of die cutting and lamination compared to adhesive transfer tapes.</p>
Application Ideas	<p>Applications where bonding silicone rubber to high surface energy materials is necessary.</p>
Application Equipment	<p>To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8).</p> <p>For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.</p>

3M™ Double Coated Tapes

9731 • 9731RW

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-223-7427 or visit www.3M.com/converter. Address correspondence to: 3M Engineered Adhesives Division, 3M Center, Building 220-7E-01, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Certification/Recognition

MSDS: 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of these products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

Important Notice

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Limitation of Remedies and Liability

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.

ISO 9002

This Engineered Adhesives Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

3M

Converter Markets
Engineered Adhesives Division

3M Center, Building 551-1W-02
St. Paul, MN 55144-1000



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2002 70-0705-7544-7 (9/02)